



PHILLYBOND #6 - TECHNICAL BULLETIN #470A EPOXY REPAIR AND PATCHING COMPOUND

Revised: 05/2018

PRODUCT DESCRIPTION

PHILLYBOND #6 is a two-component, high strength epoxy paste for the repair of punctures or cracks in tanks, pumps, pipes, steam lines, sea chests, valve bodies, etc. The material is also used to fill holes, voids and to provide a smooth surface for repairs [at temperatures up to 428°F (220°C)], PHILLYBOND #6 is resistant to most acids, alkali and hydrocarbons and will adhere to clean surfaces such as steel, cast iron, bronze, aluminum, copper, nickel, wood and most plastics.

SURFACE PREPARATION

Repair surfaces must be clean and sound and free of oil, dirt, old paint and other foreign matter. Blast, abrade or clean surface with emery cloth to rough bright finish for best adhesion. Final rinse of surface with IXT 59 solvent helps to ensure complete removal of grease and oils.

MIXING AND APPLICATION INSTRUCTIONS

Mix white resin with black hardener - four parts resin to one part hardener by weight or volume - with putty knife or similar tool until a streak-free uniform color is achieved. As PHILLYBOND #6 is a fast curing system, mix only that amount that can be used in 10-15 minutes. Apply the mixed compound to the repair area forming a cross section of at least 3/8" (9.5mm) thick. The patch should extend at least 2" (5cm) on all sides of the damaged area. PHILLYBOND #6 may be smoothed by wetting putty knife with IXT 59 solvent or water. After hardening PHILLYBOND #6 can be machined or sanded, as desired, for a smoother surface.

TECHNICAL INFORMATION

COLOR	Resin - White, Hardener - Black, Mixed - Gray
CURE TIME	1 hr @ 72°F (22°C) @ ½ inch (12.7 mm) thickness
MIXING RATIO	4:1 by volume and weight
PACKAGING	1 lb (454 gram) Kit. 10 Kits per Case
POT LIFE	10 – 15 minutes @ 72°F (22°C)
SHELF LIFE	Two years if stored in a cool, dry area
TEMPERATURE RESISTANCE	428°F (220°C)
SHEAR STRENGTH	1,000 psi (70.3 cm ² /kgf)
VISCOSITY	Paste / putty
MIL SPEC	R-17882-C

General: Every reasonable effort is made to insure the technical information and recommendations on these data pages are true and accurate to the best of our knowledge at the date of issuance. However, this information is subject to change without notice. Prior versions of this publication are invalid with the release of this version. Products and information are intended for use by qualified applicators that have the required background, technical knowledge, and equipment to perform said tasks in a satisfactory manner. Consult your local distributor for product availability, additional product information, and technical support. **Warranty:** ITW Performance Polymers, a division of Illinois Tool Works Inc., warrants that its products meet their printed specifications. This is the sole warranty. This warranty expires one year after product shipment. **Warranty Claims:** If any product fails to meet the above, ITW Performance Polymers will, at its option, either replace the product or refund the purchase price. ITW Performance Polymers will have no other liability for breach of warranty, negligence, or otherwise. All warranty claims must be made in writing within one year of the date of shipment. No other claims will be considered. **Disclaimer:** ITW Performance Polymers makes no other warranty, expressed or implied, and specifically disclaims any warranty of merchantability or fitness for a particular purpose. Suggestions concerning the use of products are not warranties. The purchaser assumes the responsibility for determining suitability of products and appropriate use. ITW Performance Polymers' sole liability, for breach of warranty, negligence or otherwise, shall be the replacement of product or refund of the purchase price, at ITW Performance Polymers' election. Under no circumstances shall ITW Performance Polymers be liable for any indirect, incidental or consequential damages. **Modification of Warranty:** No distributor or sales representative has the authority to change the above provisions. No change in the above provisions will be valid unless in writing and signed by an officer or the Technical Director of ITW Performance Polymers. No term of any purchase order shall serve to modify any provision of this document. **Mediation and Arbitration:** If any dispute arises relating to products or product warranties, either the purchaser or ITW Performance Polymers may a) initiate mediation under the then current Center for Public Resources (CPR) Model Procedure for Mediation of Business Disputes, or b) initiate a non-binding arbitration under the rules of the American Arbitration Association for the resolution of commercial disputes.

ITW PERFORMANCE POLYMERS

130 Commerce Drive | Montgomeryville | PA 18936 | USA | T: 215-855-8450 | E-mail: customerservice.na@itwpp.com | www.itwperformancepolymers.com